

HPB SUPREME BLOWN HAND FILM .63 mil

Product Description

Supreme is a premium grade blown hand film. Available in low gauges. High puncture and tear resistance. Available in widths from 11 inches to 18 inches.

Applications

Brick and block
Warehouse
Irregular loads
Transportation industry
Food distribution

Bagged products
Boxed products
All applications

SIGMA
SUPREME

Film Properties	Typical Value (English)	Tolerance	Test Method
Tensile Strength at Yield MD	1600 psi	± 15%	ASTM D882
Tensile Strength at Yield TD	1700 psi	± 15%	ASTM D882
Tensile Strength at Break MD	7000 psi	± 15%	ASTM D882
Tensile Strength at Break TD	4900 psi	± 15%	ASTM D882
Elongation at Break MD	450%	± 15%	ASTM D882
Elongation at Break TD	600%	± 15%	ASTM D882
Protrusion Puncture	7.1 lbs.	± 15%	ASTM D5748
Protrusion Puncture Energy	14.3 in-lb	± 15%	ASTM D5748
Elmendorf Tear Strength MD	160 g/mil	± 15%	ASTM 1922
Elmendorf Tear Strength TD	750 g/mil	± 15%	ASTM 1922
Cling - Outside to Inside @ 225%	min 150 g/in	± 15%	ASTM D5458

Dimensions	Value	Tolerance
Core ID	3.05 inches	± 0.05%
Film Thickness	16.0 micron	

**Manufactured with pride in the USA and Canada by
Sigma Stretch Film**

Page & Schuyler Aves. Bldg #8
Phone: 800-672-9727 • 201-507-9100
Email: stretch.info@sigmaplastics.com
Visit our website at www.sigmastretchfilm.com
©Copyright 2018 Sigma Stretch Film